

*Moisture-tolerant epoxy adhesive  
for structural bonding applications*

# webertec EP structural adhesive



## Uses

- Adhesive for structural bonding
- Jointing of precast segmental bridge units
- Adhesive for external steel plate bonding
- Adhesive for **webertec force carbon plate** composite strengthening
- Adhesive for bonding rubber bearing pads for highways and railways

## About this product

**webertec EP structural adhesive** is a two-component, bisphenol epoxy resin and polyamine hardener, highly moisture-tolerant structural adhesive for structural jointing and structural strengthening. Used for application thicknesses of 2 – 10 mm.

Conforms with BS EN 1504-4.

## Features and benefits

- ▲ Excellent cohesive bond to prepared surfaces
- ▲ Good adhesion to concrete, steel, timber, glass, rubber and carbon fibre
- ▲ Negligible shrinkage on curing
- ▲ Moisture tolerant for all year round work
- ▲ Fully complies with BA 30/94 *Strengthening of Concrete Highway Structures Using Externally Bonded Plate*

## Technical data

The following test results were obtained in laboratory conditions at 20°C

### Physical properties

Colour	Mid grey when mixed Components different colours
Density	1685 kg/m <sup>3</sup>
Temperature usage	10°C – 25°C
Cure temperature	+5°C to 30°C
Moisture resistance	0.5% water absorption at 1.1 mm 0.3% water absorption at 1.6 mm
Workable life	30 minutes at 20°C

# webertec EP structural adhesive

## Preparation

No adhesive will develop full bond adhesion strength without the surface substrate being carefully prepared to give a mechanically sound, clean surface.

### Concrete and masonry

The surface must be prepared by mechanical means, such as grinding or grit blasting, to remove any weak surface laitance or deleterious, friable material.

The substrate should have an inherent tensile strength greater than 1.0 N/mm<sup>2</sup>.

Pull-off tests should be carried out prior to application of the adhesive.

If the substrate is uneven, then the surface must be re-profiled with a levelling mortar. Check for evenness of substrate.

### Timber

Timber surfaces should be prepared by sanding and planing with all dust removed under vacuum.

### Steel substrates

These should be grit blasted to Swedish Standard SA 2<sup>1/2</sup>, equivalent to BS 7079-A1 and de-greased immediately prior to application. Where corrosion is absent, wire brushing to a clean, bright surface may be adequate. Care must be taken not to polish the rust.

## Mixing

Mix by adding the dark grey hardener to the white resin and mix for 3 to 5 minutes with a low speed drill and spiral mixing head (EPI MR4 100). Mix until a uniform consistency and colour is obtained.

In cold weather, it is advisable to store the product unopened in a warm environment for several hours before mixing.

## Application

The mixed adhesive must be placed within its pot life. Apply the adhesive to the prepared substrate with a grooved trowel or by gloved hands. Apply material to both surfaces before joining together.

In some cases, only one face needs to be coated with adhesive, provided that at least 3 mm thickness is applied (e.g. segmental bridge construction).

### Plate bonding

Push the glued plates onto the glued substrate within the open life of the material.

Apply a hard rubber roller to squeeze the adhesive from both sides of the plate edge and ensure no air voids.

Roller to achieve a bond line of approximately 2 – 3 mm thickness. Remove the surplus adhesive from the sides of the plate.

### Setting time

Temp	
5°C	Do not use
10°C	80 minutes
15°C	65 minutes
20°C	44 minutes
25°C	31 minutes

## Cleaning

Clean tools and any uncured adhesive using **webertec solvent**.

## Packaging

**webertec EP structural adhesive** is available in 5 kg pails with hardener compound recessed in the lid.

## Coverage

Yield 5 kg approximately 2.9 litres.

Thickness of adhesive	kg/m <sup>2</sup>
2 mm	3.3
4 mm	6.7
10 mm	17.0

## Storage and shelf life

Shelf life is at least 12 months when it is kept unopened and stored in cool, dry conditions.

Store at between 5°C and 25°C.

**Protect from frost.**

## Health and safety

Contains epoxy constituents. Refer to information supplied by manufacturer (see Material Safety Data Sheet).

All skin contact with epoxy resin products should be avoided. Barrier creams should be used and operatives should wear protective clothing including gloves. Working areas should be well ventilated.

The hardener content is alkaline and labelled as corrosive. The resin content is labelled as an irritant. The flash point of all components is in excess of 100°C. In the event of fire use foam, dry chemical, carbon dioxide (CO<sub>2</sub>) or water fog extinguishers.

**For further information, please request the Material Safety Data Sheet for this product.**

## Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

### Technical helpline

Tel: 08703 330 070  
e-mail: [technical@netweber.co.uk](mailto:technical@netweber.co.uk)

## Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

### UK and Ireland

Tel: 08703 330 070  
Fax: 0800 014 2995  
e-mail: [sales@netweber.co.uk](mailto:sales@netweber.co.uk)

### Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK  
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: [mail@netweber.co.uk](mailto:mail@netweber.co.uk)  
[www.netweber.co.uk](http://www.netweber.co.uk)

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.