

White travertine finish

alpine



About this product

alpine finish is a white cement based mix containing aggregates that provides a decorative travertine finish.

Technical data

Suitable specification clauses for dealing successfully with most types of substrates are available from our Technical Services Department.

BS 5262, *Code of practice for external renderings*, and BS 8000-10, *Workmanship on building sites. Code of practice for plastering and rendering* should be followed at all times.

Fire resistance

alpine is non-combustible and would be expected to meet a Class 0 fire rating when applied to non-combustible substrates.

Uses

- Enhances the protection of a traditional rendering system
- Suitable for external or internal use
- Ideal for application onto primed **weberend OCR** or other cement based render

Constraints

Do not apply to gypsum plaster or previously painted surfaces.

Features and benefits

- ▲ Excellent weather resistance and durability
- ▲ Low maintenance white finish
- ▲ May be over-painted when dry with a suitable masonry paint if required
- ▲ Easy and quick to apply
- ▲ Simple to finish

alpine

Preparation

All surfaces must be sound, clean, dry and free from any material which may impair adhesion, and lightly floated to provide key. Scaffolding must be independently tied to allow uninterrupted application. Any faults in the structure, particularly those which may lead to moisture penetration, must be rectified.

To avoid dampness and discolouration rendering should be avoided below DPC or within 150 mm of ground level.

All surfaces must be suction free to ease application and texturing as well as accentuating the whiteness of the material. For this purpose, prime the surface with either white **weber PR310** or a dilution of 1 part **webertec latex**.

alpine must be applied before the priming coat has fully dried.

Mask around the areas where material is to be applied. Masking tape must be removed before the material has dried out.

Mixing

Mix with clean water at a rate of approximately 6 litres per 25 kg bag, using a clean tumble mixer or suitable drill with whisk attachment.

Mix for 3 – 4 minutes to give a workable consistency. Allow to stand for 10 – 15 minutes before re-mixing for maximum workability.

Mix only sufficient material for use within the hour.

To ensure colour consistency, the materials required for complete and adjoining panels should be of the same batch number or be thoroughly mixed together before use.

Application

Trowel apply **alpine** as a tight coat while the primer is still tacky. When being properly spread, the material tends to 'chatter' under the trowel.

To obtain the travertine texture, draw a wood float across the face of the work with the minimum of pressure, in sharp horizontal or vertical strokes in one direction only. It is essential that this is carried out before the material stiffens on the wall.

As a contrast, the reveals to doors and windows may be 'dragged' vertically when the main areas are textured horizontally.

To obtain the circular texture, the material should be finished with a light circular action.

To prevent joints from showing, application should be continuous up to angles or features.

To maintain the texture at internal angles or close to soffits, the edge of the float should be pulled lightly in short strokes away from the angle.

Curing with a fine spray of clean water may be necessary during rapid drying conditions. In hot climates curing is essential for 3 – 5 days after application.

Protection

Protect from unfavourable weather conditions during application and early curing.

Good practice

Do not apply:

- If frost is forecast within 24 hours of use
- In damp/wet conditions
- In temperatures below 5°C or above 30°C
- On elevations in direct sunlight or where the substrate is hot

Cleaning

Clean equipment by washing immediately after use with clean water. Do not dispose of waste material into drainage systems.

Packaging

alpine is supplied in 25 kg bags.

Coverage

alpine: For each mm of thickness, you will require approximately 1.52 kg per m². When applied at the correct thickness of 3 mm, coverage is approximately 5 – 6 m² per 25 kg bag.

Priming coat: Approximately 4 m² per litre of **white weber PR310** or 15 – 20 m² per litre of **webertec latex** after dilution 1:3 with water.

Note: These estimates take no account of wastage and may vary according to the type of surface involved.

Storage and shelf life

When stored unopened in a dry place at temperatures above 5°C, shelf life is 12 months from date of manufacture.

Health and safety

Contains cement (Contains chromium (VI)). May produce an allergic reaction. Harmful by inhalation. Irritating to eyes and skin. Keep out of the reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical help. After contact with skin, wash immediately with plenty of soap and water. Wear suitable protective clothing, gloves and eye/face protection.

For further information, please request the Material Safety Data Sheet for this product.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline

Tel: 08703 330 070
e-mail technical@netweber.co.uk

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

UK and Ireland

Tel: 08703 330 070
Fax: 0800 014 2995
e-mail sales@netweber.co.uk

Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: mail@netweber.co.uk
www.netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.